



ROUND PIPES ASTM A312, A778 - EN 10217-7

Tubi tondi ASTM A312, A778 - EN 10217-7

NPS	outside diameter mm	standard ANSI B 36-19					
		schedule 5S		schedule 10S		schedule 40S	
		wall thickness and weight					
		mm	kg/m	mm	kg/m	mm	kg/m
3/8"	17,15			1,65	0,640	2,31	0,858
1/2"	21,34	1,65	0,814	2,11	1,016	2,77	1,288
3/4"	26,67	1,65	1,034	2,11	1,298	2,87	1,710
1"	33,4	1,65	1,312	2,77	2,125	3,38	2,541
1 1/4"	42,16	1,65	1,674	2,77	2,732	3,56	3,441
1 1/2"	48,26	1,65	1,926	2,77	3,155	3,68	4,108
2"	60,33	1,65	2,424	2,77	3,992	3,91	5,524
2 1/2"	73,03	2,11	3,747	3,05	5,345	5,16	8,769
3"	88,9	2,11	4,585	3,05	6,557	5,49	11,466
3 1/2"	101,6	2,11	5,256	3,05	7,526	5,74	13,778
4"	114,3	2,11	5,927	3,05	8,496	6,02	16,322
6"	168,28	2,77	11,480	3,40	14,037	7,11	28,694
8"	219,08	2,77	15,003	3,76	20,272	8,18	43,198
10"	273,05	3,40	22,957	4,19	28,208		
12"	323,85	3,96	31,720	4,57	36,536		
14"	355,6	3,96	34,868	4,78	41,990		